


(株) 중화케미칼



Thermoplastic Polyurethane Elastomer

熱塑性聚氨基酯彈性體

TPU

TPU FOR INK (General Grade)



Article	Density	Hardness (shore A)	100% Modulus (kg/cm ²)	Tensile strength (kg/cm ²)	Elongation (%)	Viscosity range 30% solid content in Anone (cps /25℃)
A7810H	1.18 ± 0.02	77 ± 2	35	200	700	20,000~30,000
A7810	1.18 ± 0.02	77 ± 2	35	150	700	10,000~15,000
A7810L	1.18 ± 0.02	77 ± 2	35	100	700	3,000~5,000
A8510H	1.18 ± 0.02	85 ± 2	70	200	600	20,000~30,000
A8510	1.18 ± 0.02	85 ± 2	70	150	600	10,000~15,000
A8510L	1.18 ± 0.02	85 ± 2	70	100	600	3,000~5,000
A8511H	1.18 ± 0.02	85 ± 2	70	200	600	20,000~30,000
A9513H	1.18 ± 0.02	95 ± 2	90	450	400	20,000~30,000

TPU FOR INK (Hydrolysis Resistance Grade)



Article	Density	Hardness (shore A)	100% Modulus (kg/cm ²)	Tensile strength (kg/cm ²)	Elongation (%)	Viscosity range 30% solid content in Anone (cps /25°C)
A7020	1.18 ± 0.02	72 ± 2	35	200	800	Anone / MEK (50 / 50) 3,000~4,000
A7710	1.18 ± 0.02	77 ± 2	35	200	900	4,000~6,000
A7711	1.18 ± 0.02	77 ± 2	35	250	800	16,000~24,000
A8521H	1.18 ± 0.02	85 ± 2	75	300	650	20,000~25,000
A8521	1.18 ± 0.02	85 ± 2	75	250	650	10,000~15,000

PS : The above are just for general reference and could not be used as guarantee document.

감사합니다 !



(株) 중화케미칼

135-915 서울시 강남구 역삼동 677-12번지 선빌딩
202호

Tel : 02-539-6188 Fax : 02-539-8488

Email : junghwa@junghwachemical.com

Website : www.junghwachemical.com